Recommended Construction Material Sources for District Mirpur

OF.NO			H	2	ω	4	U			O
DISTRICT						rpur	M			
sand sources	Local sources have marginal use (<2000psi	strength)	Jatlan sand							
ources	out of District		Chinab sand				Lawrencepur/	Qibla bandi sand deposit		
Coarse Agg	Local sources have marginal use (<2000psi	strength)	Khari Sharief	Mangla jatli road	Jeri Kas	Sakater	Kanali Kas	Ganoi Kas	Kot Sarsawa	Hari kas
coarse Aggregate Source	out of district					Margalla Hill	limestone			
Stone to	Local		No. of Contraction		Jeri Kas	Sakater	Kanali Kas	Ganoi Kas	Kot Sarsawa	Hari kas
stone for masonry	out of district					0 0 0 0 0 0 0 0 0 0 0 0 0 0 0 0 0 0 0				
ciay de	Local			ress	n prog	oosit is	clay de	tudy of	S	
masonry	out of district					Rawalpindi	Peshawar			
Stone soling of roads	Local				Jeri Kas	Sakater	Kanali Kas	Ganoi Kas	Kot Sarsawa	Hari kas
or roads	out of district					0 0 0 0 0 0 0 0 0 0 0 0 0 0 0 0 0 0 0		-		
for Asph	Local									
Coarse aggregate for Asphalt/premix used in roads	Out of district					Margalla Hill	limestone			

Note: 1. Recommended sources for coarse aggregate within district are from nullah bed/ alluvial deposit and Soan formation where proper size stone selection for masonery purpose is required which depends upon the size 10"+.

- 2. Ordinary Portland Cement (OPC) available in local market consist of 0.5 to 0.8% alkalies.
- 3. To avoid the Alkali Silica Reaction (OPC) can be replaced with Pozolona, slag or low alkali cement which should meet the 10000psi strength (BS-12, ASTM C150).
- 4. (i) Steel testing on each consignment is required to meet the ASTM 615A where for grade 40 steel required yield strength is 40,000psi and for grade 60 required yield strength is 60,000psi.
- (ii) Chemical tests of the steel should meet the ASTM 706A.
- 5. Other local quarries material should be evaluated as per ranges provided in Table 4.1
- 6. Material of fine & coarse aggregate not fulfill the evaluation criteria mentioned in Table 4.1 should be treated as rejected.

7. For more detail visit our website www.pndajk.gov.pk

Geologist Inyms 12/1/2011.

Rate Analysis Section

Chief Rate Analysis Section

STUDY OF CONSTRUCTION MATERIAL SOURCES IN AJK Table 4.1 Criteria Used for Evaluating the Material Sources

	CONCRETE COARSE AGGREGATES		Traffic	Roads+	*Ten	*Tentative Limits Medium Traffic	ROAD AGGREGATE ve Limits	REGATE	raffic		ASHTO	TRL		ASTM	FINE	5	NGGREG	FINE AGGREGATES BS Mortar and Plast
PHYSICAL ENGINEERING		Heavy	Heavy Traffic Roads†	Roads†	Me	dium Tra Roads†	ffic	Light.	Light Traffic R	Roads†	AASHT	Ħ		LIMITS		100	Mortar	Mortar and Plaster
PARAMETERS	ASTM C-33 SPECIFICATION LIMITS	bound	ing Course	inous /Sub-base	nbound	ing Course	ninous /Sub-base	nbound	ring Course	ninous /Sub-base	pe of roads	ninous Mixes		Aggregate for oncrete and Mortar	onry Mortar	12	r Screed	r Screed rnal Rendering
		All Unt	Wearin	Bitumi Base/S	All Uni	Weari	Bitumi Base/	All Un	Weari		All typ	Bitum	Unbo		Maso		Floor	20000
Specific Gravity (not less than)	2.5	ALLEH HORE																
Water Absorption (not more than. %)																		
Sodium Sulfate Soundness (max. %)	12									A		12			a la visit	and the same of the		A CONTRACTOR OF THE PROPERTY O
Los Angeles Abrasion Value (max. %)	50	25	25	မ	30	30	35	35	30	35		30	35					County was a state of the state
Materials Passing (No.200 sieve) (% by wt.)	S													3				
Shale (% by wt.)																		
Clay Lumps and Friable Particles (% by wt.)	2								District of the second of the					w	The state of the s	artinian		
Other Deleterious Substances (% by wt.)	_													The state of the s		ORGANIAN.		
Impact Value (max.)		23	23	30	27	27	30	30	27	30		25						
Crushing Value (max.)		23	23	30	27	30	30	30	27	30		25		The state of the s				
10% Fine Value kN (min.) Dry		130	130	100	115	100	100	100	115	100	150		110			111111		
10% Fine Value kN (min.) Soaked		80	00	50	65	65	50	50	65	50				Continues of the Contin				
Flakiness (max.)	410											45	35					
Sand Grading	and the second s													ASTM C-33	BS- 1200	-	BS-112	BS-112 BS- 1199
Fineness Modulus														ASTM C-33				
Mortar Bar Expansion % (max.) at 14 days (ASTM 1260)	0.1													0.1		L		
Bitumen Adhesion (Not less than)											95	75						



Minimum Required Parameters for Brick Selection

S.No.	Class Of Brick	Weight Of Brick (lbs) (Bone Dry)	Size Of Brick (inch X inch X inch)	Water Absorption Ratio	Strength Of Brick (psi)
1	1st Class	7	9 X 4-1/2 X 3	1/6 th of its dry Weight	1200 to 1500
2	2 nd Class	7	9 X 4-1/2 X 3	1/4 th of its dry Weight	900 to 1200
3	3 rd Class	6.75	9 X 4-1/2 X 3	1/3 rd of its dry Weight	500 to 900
4	4 th Class	7.2	9 X 4-1/2 X 3	1/2.5 of its dry Weight	Less than 500

Chief Rate Analysis 22/7/2011

Planning And Dev. Deptt

Govt. Of AJK M.abad